

IN THE CLAIMS

*The status of the claims as presently amended is as follows:*

1. *(Canceled)*
  
2. *(Currently Amended)* The substrate according to claim [[1]] 3, wherein the soft magnetic underlayer has a thickness of 3  $\mu\text{m}$  or greater.
  
3. *(Previously Presented)* A substrate for a perpendicular magnetic recording medium, the substrate comprising:
  - a nonmagnetic base composed of an aluminum alloy;
  - a soft magnetic underlayer; and
  - a nonmagnetic underlayer composed of an Ni-P alloy formed between the base and the soft magnetic underlayer,
 wherein the soft magnetic underlayer consists of a Ni-P alloy containing phosphorus in a range of 0.5 wt% to 6 wt%.
  
4. *(Original)* The substrate according to claim 3, wherein the nonmagnetic underlayer has a thickness ranging 0.5  $\mu\text{m}$  to 7  $\mu\text{m}$ , the soft magnetic underlayer has a thickness of 0.3  $\mu\text{m}$  or greater, and a sum of the thickness of the nonmagnetic underlayer and the thickness of the soft magnetic underlayer is 3  $\mu\text{m}$  or greater.
  
5. *(Original)* The substrate according to claim 3, wherein the nonmagnetic underlayer is composed of Ni-P alloy containing about 11 wt% of phosphorus.
  
6. *(Currently Amended)* The substrate according to claim [[2]] 3, wherein the surface of the soft magnetic underlayer has a surface roughness Ra of 0.5 nm or less and a micro waviness Wa of 0.5 nm or less.
  
7. *(Original)* The substrate according to claim 4, wherein the surface of the soft magnetic underlayer has a surface roughness Ra of 0.5 nm or less and a micro waviness Wa of 0.5 nm or less.
  
8. *(Canceled)*

9. (*Currently Amended*) The perpendicular magnetic recording medium according to claim [[8]].  
10, wherein the soft magnetic underlayer has a thickness of 3  $\mu\text{m}$  or greater.

10. (*Previously Presented*) A perpendicular magnetic recording medium comprising:

a substrate; and

a nonmagnetic seed layer, a magnetic recording layer, and a protective layer  
sequentially formed on the substrate,

wherein the substrate comprises a nonmagnetic base composed of an aluminum alloy, a  
soft magnetic underlayer, and a nonmagnetic underlayer composed of an Ni-P alloy formed  
between the base and the soft magnetic underlayer,

wherein the soft magnetic underlayer consists of a Ni-P alloy containing phosphorus in a  
range of 0.5 wt% to 6 wt%, and

wherein the soft magnetic underlayer functions as a soft magnetic backing layer.

11. (*Original*) The perpendicular magnetic recording medium according to claim 10, wherein the  
nonmagnetic underlayer has a thickness ranging 0.5  $\mu\text{m}$  to 7  $\mu\text{m}$ , the soft magnetic underlayer  
has a thickness of 0.3  $\mu\text{m}$  or greater, and a sum of the thickness of the nonmagnetic underlayer  
and the thickness of the soft magnetic underlayer is 3  $\mu\text{m}$  or greater.

12. (*Original*) The perpendicular magnetic recording medium according to claim 10, wherein the  
nonmagnetic underlayer is composed of Ni-P alloy containing about 11 wt% of phosphorus.

13. (*Currently Amended*) The perpendicular magnetic recording medium according to claim [[9]].  
10, wherein the surface of the soft magnetic underlayer has a surface roughness Ra of 0.5 nm  
or less and a micro waviness Wa of 0.5 nm or less.

14. (*Original*) The perpendicular magnetic recording medium according to claim 11, wherein the  
surface of the soft magnetic underlayer has a surface roughness Ra of 0.5 nm or less and a  
micro waviness Wa of 0.5 nm or less.

15. (*Currently Amended*) The perpendicular magnetic recording medium according to claim [[8]].  
10, further including a soft magnetic supplement layer between the soft magnetic underlayer of

the substrate and the nonmagnetic seed layer, wherein the soft magnetic supplement layer has a film thickness of 50 nm or less, and a product of the film thickness and a saturation magnetic flux density is 150 G  $\mu\text{m}$  or larger.

16. (*Canceled*)

17. (*Withdrawn - Currently Amended*) The method according to claim [[16]] 18, wherein the soft magnetic underlayer has a thickness of 3  $\mu\text{m}$  or greater.

18. (*Withdrawn - Currently Amended*) A method of manufacturing a substrate for a perpendicular magnetic recording medium, the method comprising the steps of:  
providing a nonmagnetic base composed of an aluminum alloy;  
electroless plating a nonmagnetic underlayer composed of an Ni-P alloy on the nonmagnetic base; and  
electroless plating a soft magnetic underlayer consisting of a Ni-P alloy containing phosphorus in a range of 0.5 wt% to [[4]] 6 wt% on the nonmagnetic underlayer.

19. (*Withdrawn*) The method according to claim 18, wherein the nonmagnetic underlayer has a thickness ranging 0.5  $\mu\text{m}$  to 7  $\mu\text{m}$ , the soft magnetic underlayer has a thickness of 0.3  $\mu\text{m}$  or greater, and a sum of the thickness of the nonmagnetic underlayer and the thickness of the soft magnetic underlayer is 3  $\mu\text{m}$  or greater.

20. (*Withdrawn - Currently Amended*) The method according to claim [[16]] 17, further comprising the step of heating the substrate to a temperature of 300° C or less for 30 minutes or longer after forming the soft magnetic underlayer.

21. (*Withdrawn*) The method according to claim 18, further comprising the step of heating the substrate to a temperature of 300° C or less for 30 minutes or longer after forming the soft magnetic underlayer.

22. (*Withdrawn - Currently Amended*) The method according to claim [[17]] 18, further including the step of polishing the surface of the soft magnetic underlayer using free abrasive grains to smooth the surface thereof.

23. (*Withdrawn*) The method according to claim 19, further including the step of polishing the surface of the soft magnetic underlayer using free abrasive grains to smooth the surface thereof.

24. (*Withdrawn - Currently Amended*) The method according to claim ~~[[22]]~~ 18, wherein the surface of the soft magnetic underlayer has a surface roughness Ra of 0.5 nm or less and a micro waviness Wa of 0.5 nm or less.

25. (*Withdrawn*) The method according to claim 23, wherein the surface of the soft magnetic underlayer has a surface roughness Ra of 0.5 nm or less and a micro waviness Wa of 0.5 nm or less.

26. (*Canceled*)

27. (*Withdrawn - Currently Amended*) The method according to claim ~~[[26]]~~ 28, wherein the soft magnetic underlayer has a thickness of 3  $\mu\text{m}$  or greater.

28. (*Withdrawn*) A method of manufacturing a perpendicular magnetic recording medium comprising the steps of:

forming a substrate by providing a nonmagnetic base composed of an aluminum alloy, electroless plating a nonmagnetic underlayer composed of an Ni-P alloy on the nonmagnetic base, and electroless plating a soft magnetic underlayer consisting of a Ni-P alloy containing phosphorus in a range of 0.5 wt% to 6 wt% on the nonmagnetic underlayer;

texturing a surface of the soft magnetic underlayer using free abrasive grains; and sequentially forming a nonmagnetic seed layer, a magnetic recording layer, and a protective layer by sputtering.

29. (*Withdrawn*) The method according to claim 28, wherein the nonmagnetic underlayer has a thickness ranging 0.5  $\mu\text{m}$  to 7  $\mu\text{m}$ , the soft magnetic underlayer has a thickness of 0.3  $\mu\text{m}$  or greater, and a sum of the thickness of the nonmagnetic underlayer and the thickness of the soft magnetic underlayer is 3  $\mu\text{m}$  or greater.

30. (*Withdrawn - Currently Amended*) The method according to claim ~~[[26]]~~ 27, further comprising the step of heating the substrate to a temperature of 300° C or less for 30 minutes or longer after forming the soft magnetic underlayer.

31. (*Withdrawn*) The method according to claim 28, further comprising the step of heating the substrate to a temperature of 300° C or less for 30 minutes or longer after forming the soft magnetic underlayer.

32. (*Withdrawn*) The method according to claim 28, further including the step of forming a soft magnetic supplement layer on the soft magnetic underlayer before forming the nonmagnetic seed layer, wherein the soft magnetic supplement layer has a film thickness of 50 nm or less, and a product of the film thickness and a saturation magnetic flux density is 150 G·μm or larger.

33. (*Withdrawn - Currently Amended*) The method according to claim ~~[[27]]~~ 28, wherein the surface of the soft magnetic underlayer has a surface roughness Ra of 0.5 nm or less and a micro waviness Wa of 0.5 nm or less.

34. (*Withdrawn*) The method according to claim 29, wherein the surface of the soft magnetic underlayer has a surface roughness Ra of 0.5 nm or less and a micro waviness Wa of 0.5 nm or less.